

# Data sheet: SkamoWall Board

---

Grade	Value	Unit
Bulk density (EN 1602)	225	kg/m <sup>3</sup>
Compressive stress (EN 826)	2,800	KPa
Total porosity (EN 993-1)	91	%
Water vapour transmission, $\mu$ (EN 12086)	3	
Short term water absorption (EN 1609)	28	kg/m <sup>2</sup>
Thermal conductivity (EN 12667), $\lambda_{23,50}$	0.068	W/(m×K)
Fire classification (EN 13501-1:2007 + A1:2009)	A1	
HS Tariff number (Harmonized Commodity Description and Coding System)	6806.90.00	
Colour	Grey	

Data are average results of tests conducted under standard procedures and are subject to variation.

Data contained in this data sheet are supplied in good faith as a technical service and are subject to change without notice. Misprint and errors excepted.

Revision number: 14-03-2018

## Skamol

Østergade 58-60, 7900 Nykøbing Mors, Denmark

Tel.: +45 97 72 15 33

[www.skamol.com](http://www.skamol.com)

